## **Product Information**





## Mylar® A 190 - 500μm

## **Product Description**

MYLAR® polyester film is a flexible, strong and durable film with an unusual balance of properties making it suitable for many industrial applications. Type MYLAR® A is a tough general purpose film available in  $12\mu m$  to  $500\mu m$  thickness range. In film thickness  $12\mu m$  to  $125\mu m$ , MYLAR® A is slightly hazy. In film thicknesses  $190\mu m$  and above, MYLAR® A is hazy. Type MYLAR® A is primarily used for release applications, office supplies, electrical insulation and industrial laminations with other flexible materials.

## Film Properties (typical values)

Type MYLAR® A has a tensile strength that averages 210 MPa, has excellent resistance to moisture and most chemicals and can withstand temperature extremes from -70°C to 150°C. Because it contains no plasticisers MYLAR® A does not become brittle with age under normal conditions.

Property	<b>Test Method</b>		Value				
Thickness		micron	190	250	300	350	500
Tensile Strength (Mpa)	<b>ASTM D 882</b>	MD	190	190	190	190	150
		TD	220	200	200	190	170
Modulus (Mpa)	<b>ASTM D 882</b>	MD	3300	3100	3000	2950	2600
		TD	3700	3500	3200	3200	2800
Elongation (%)	<b>ASTM D 882</b>	MD	190	210	210	240	270
		TD	140	170	180	200	240
Shrinkage 150°C for 30 min (%)	ASTM D 1204	MD	1.3	1.3	1.3	1.3	0.9
		TD	1.3	1.3	1.3	1.3	0.9
Shrinkage 200°C for 30 min (%)	ASTM D 1204	MD	3.5	3.5	3.5	3.5	2
		TD	3.3	3.3	3.5	3.3	1.7
Haze (%)	ASTM D 1003		82	90	92	96	97
	Gardner Hazemeter						
Dielectric Strength	<b>ASTM D 149</b>		17.5	19	19.5	20	20
(minimum) (kV)							

 $1 \, mm = 1 \, \, micron = 0.001 \, \, mm \, \, approx \, 4 \, \, gauge, \, MD = Machine \, \, Direction, \, TD = Transverse \, \, Direction$ 

Enquiries should be addressed to:

DuPont Teijin Films (Luxembourg) SA

BP 1681

L-1016 Luxembourg Telephone: +352 2616 4004 Fax No: +352 2616 5000 This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont Teijin Films makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.



**Caution:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Teijin Films Medical Caution Statement", H-50102-DTF.

Melinex®, Kaladex®, Mylar®, Cronar® and Teonex® are registered trademarks of DuPont Teijin Films. Only DuPont Teijin Films makes Melinex® brand, Kaladex® brand, Mylar® brand, Cronar® brand and Teonex® brand films.



Mylar<sup>®</sup> Only by DuPont Teijin Films